

TEST REPORT

Test Report # 20W-008630 Date of Report Issue: August 24, 2020
Date of Sample Received: July 15, 2020 Pages: Page 1 of 13

CLIENT INFORMATION:

Company: BIC Graphic
Recipient: 14421 Myerlake Circle
Clearwater
Florida
33760
United States (USA)



SAMPLE INFORMATION:

Description: KOOZIE® Olympus Cooler Tote (New Color)
Assortment: - Test Request Form No.: 4147_HK
Item No.: 16017 Country of Origin: China
Shipment Order No.: PO#7106611 Labeled Age Grade: -
Country of Distribution: Canada, United States Requested Age Grade: -
Quantity Submitted: 2 pcs per color Tested Age Grade: -
Testing Period: 07/16/2020-07/23/2020

OVERALL RESULT:

PASS

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.

Contrary Kong

Contrary Kong
Chemical Laboratory Manager



TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Paints and Surface Coatings
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	CPSC 16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates(DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	Canadian Phthalates Regulations SOR/2016-188, Phthalates (DBP, BBP, DEHP, DnOP, DINP, DIDP) in Mouthable Vinyl Materials
PASS	Client’s Requirement, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)
PASS	FDA 21 CFR 177.1350, Ethylene-Vinyl Acetate Copolymers



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with ‘φ’ was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4a	5a	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	41	39	---	---	---	90
Conclusion	PASS	PASS	---	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
4a	Black coating	Black metal zipper pull(all styles)
5a	Black coating	Black zinc metal bottle opener(all styles)



DETAILED RESULTS:

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4a	5a	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	41	39	---	---	---	90
Conclusion	PASS	PASS	---	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15mg/kg)

Remark:

The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
4a	Black coating	Black metal zipper pull(all styles)
5a	Black coating	Black zinc metal bottle opener(all styles)



DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4b	5b	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	28	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:
 mg/kg = Milligrams per kilogram
 LT = Less than
 ND = Not detected (Reporting Limit = 15 mg/kg)

Remark:
 The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
3	Black textile	Black pp plastic handle and strap(all styles)
4b	Silver metal	Black metal zipper pull(all styles)
5b	Silver metal	Black zinc metal bottle opener(all styles)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4a	5a	---	---	---	Total Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	41	39	---	---	---	90
Total Mercury (Hg)	ND	ND	---	---	---	10
Conclusion	PASS	PASS	---	---	---	

Note:
 mg/kg=Milligrams per kilogram
 LT = Less than
 ND = Not detected (Reporting Limit: Pb=15 mg/kg; Hg = 10 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
4a	Black coating	Black metal zipper pull(all styles)
5a	Black coating	Black zinc metal bottle opener(all styles)



DETAILED RESULTS:

Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4b	5b	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	28	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	---	---	---	---	90
Conclusion	PASS	---	---	---	---	

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
3	Black textile	Black pp plastic handle and strap(all styles)
4b	Silver metal	Black metal zipper pull(all styles)
5b	Silver metal	Black zinc metal bottle opener(all styles)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	6	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	---	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	---	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	---	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	6	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:
 mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)
 LT = Less than
 ND = Not detected (Reporting Limit = 150 mg/kg)

Remark:
 The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

Canadian Phthalates Regulations SOR/2016-188, Phthalates (DBP, BBP, DEHP, DnOP, DINP, DIDP) in Mouthable Vinyl Materials

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Vinyl material foreseeable be placed in the mouth

Specimen No.		1	2	6	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:
 mg/kg = Milligrams per kilogram
 LT = Less than
 ND = Not detected (Reporting Limit = 150 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

Client's Requirement, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	6	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Charcoal soft plastic	Charcoal Tarpaulin material main body(Charcoal style)
2	Mint soft plastic	Mint Tarpaulin material main body(Mint style)
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



DETAILED RESULTS:

FDA 21 CFR 177.1350, Ethylene-Vinyl Acetate Copolymers

Test Method: FDA 21 CFR 177.1350

Specimen No.			6	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	24 h	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	70°F	0.5 h	ND	0.1	0.5
8% Ethanol extractive (mg/in ²)	120°F	24 h	ND	0.1	0.5
50% Ethanol extractive (mg/in ²)	120°F	24 h	ND*	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in²= Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1350 (b) (1).

*The chloroform-soluble extractive analysis was conducted.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
6	Silver soft plastic(PEVA)	Silver Koozie logo PEVA lining(all styles)



SAMPLE PHOTO:



-End Report-

